

AD-A266 749



MENTATION PAGE

Form Approved

OMB No. 0704-0188

is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this burden estimate, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Avenue, Alexandria, VA 22304-6145. Paperwork Reduction Project (0704-0188), Washington, DC 20503

REPORT DATE

6/17/93

3. REPORT TYPE AND DATES COVERED

Final Report May 15, '92-March 14, '93

4. TITLE AND SUBTITLE

Fullerene Superconductors

5. FUNDING NUMBERS

DAAL03-92-G-0188

6. AUTHOR(S)

Richard B. Kaner

DTIC
ELECTE
JUL 09 1993

7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)

Department of Chemistry and Biochemistry
University of California, Los Angeles
Los Angeles, California 90024-1569

8. PERFORMING ORGANIZATION
REPORT NUMBER

9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES)

U. S. Army Research Office
P. O. Box 12211
Research Triangle Park, NC 27709-2211

10. SPONSORING / MONITORING
AGENCY REPORT NUMBER

ARO 29708.7-CH

11. SUPPLEMENTARY NOTES

The view, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.

12a. DISTRIBUTION / AVAILABILITY STATEMENT

Approved for public release; distribution unlimited.

12b. DISTRIBUTION CODE

13. ABSTRACT (Maximum 200 words)

98 7 08 145

The electrical, magnetic and optical properties of the fullerene superconductors K_3C_{60} and Rb_3C_{60} have been investigated. The room temperature microwave resistivity at 60 GHz of pressed powder samples of K_3C_{60} is approximately $5m\Omega cm$. The resistivity drops by almost one order of magnitude on cooling to 20K, indicative of metallic behavior, before the samples superconduct at $T_c = 19.3K$. Optical reflectivity spectra are consistent with metallic materials. An extrapolation of the frequency dependence of conductivity leads to d.c. conductivities of $1.3 \times 10^3 (\Omega cm)^{-1}$ and $1.2 \times 10^3 (\Omega cm)^{-1}$ for K_3C_{60} and Rb_3C_{60} , respectively. The gap values Δ of $24 cm^{-1}$ for K_3C_{60} and $30 cm^{-1}$ for Rb_3C_{60} are consistent with weak-coupling and a BCS singlet ground state. Upper critical fields of 28-30 Tesla for K_3C_{60} and 38-55 Tesla for Rb_3C_{60} have been measured. The lower values are from static magnetic experiments, while the upper values used pulsed magnets.

93-15563



14. SUBJECT TERMS

15. NUMBER OF PAGES

2

16. PRICE CODE

17. SECURITY CLASSIFICATION
OF REPORT

UNCLASSIFIED

18. SECURITY CLASSIFICATION
OF THIS PAGE

UNCLASSIFIED

19. SECURITY CLASSIFICATION
OF ABSTRACT

UNCLASSIFIED

20. LIMITATION OF ABSTRACT

UL

Publications resulting from "Fullerene Superconductors"
Funding Document DAAL03-92-G-0188

O. Klein, G. Grüner, S.M. Huang, J.B. Wiley and R.B. Kaner, "The electrical resistivity of K_3C_{60} ," *Phys. Rev. B.*, **46**, 11, 247 (1992). (3 pages)

S. Foner, E.J. McNiff, Jr., D. Heiman, S.-M. Huang, and R.B. Kaner, "Measurements of the upper critical field of K_3C_{60} and Rb_3C_{60} powder to 60 T", *Phys. Rev. B.*, **46**, 14, 936 (1992). (4 pages)

C.E. Johnson, H.W. Jiang, K. Holczer, R.B. Kaner, R.L. Whetten and F. Diederich, "Upper critical field-temperature phase diagram of alkali-intercalated C_{60} superconductors," *Phys. Rev. B.*, **46**, 5880 (1992). (3 pages)

E.G. Gillan, C. Yeretdzian, K.S. Min, M.M. Alvarez, R.L. Whetten, and R.B. Kaner, "Endohedral rare-earth fullerene complexes," *J. Phys. Chem.*, **96**, 6869 (1992). (4 pages)

L. Degiorgi, P. Wachter, G. Grüner, S.-M. Huang, J. Wiley, and R.B. Kaner, "Optical response of the superconducting state of K_3C_{60} and Rb_3C_{60} ," *Phys. Rev. Lett.*, **69**, 2987 (1992). (4 pages)

L. Degiorgi, G. Grüner, P. Wachter, S.-M. Huang, J. Wiley, R.L. Whetten, R.B. Kaner, K. Holczer and F. Diederich, "Electrodynamic response of Rb_3C_{60} " *Phys. Rev. B.*, **46**, 11, 250 (1992). (4 pages)

DTIC QUALITY INSPECTED 5

Personnel Supported

Ed Gillan

Olivier Klein (Ph.D. earned Fall 1992)

Accession For	
NTIS	ORASI <input checked="" type="checkbox"/>
DTIC	TAB <input type="checkbox"/>
Justification	<input type="checkbox"/>
By	
Distribution	
Availability Codes	
Dist	Availability for Special
A-1	